

# **CONIPUR EPDM 1-3.5mm**

# Granules for the In-Situ Construction of Running Tracks and Multi-Purpose Playgrounds

#### **Product description**

CONIPUR EPDM 1-3.5mm granules are applied with pavers, broadcasted or compacted by hand for the construction of sports-floorings,

## Fields of application

CONIPUR EPDM 1-3.5mm is used – together with a CONIPUR binder or CONIPUR coating – for the in-situ

construction of running tracks, multi-purpose surfaces or playgrounds.


#### **Properties**

CONIPUR EPDM 1-3.5mm granules are available in different colours.

The granules are durable, flexible, of high quality and easy to apply.

#### **Technical data**

specific weight, grain size 1-3.5mm	kg/dm <sup>3</sup>	1.6 +/- 0.03
bulk density, grain size 1-3.5mm	g/l	670 +/- 10
polymer content	%	≥ 22
tensile strength	N/mm <sup>2</sup>	>5
elongation	%	>500
hardness	Shore A	60 +/- 5
Above figures are guide values and must not be used as a base for specifications!		



# Pack size

CONIPUR EPDM 1-3.5mm is delivered in bags at 25kg.

### Colour

red, further colours on request

#### Storage

CONIPUR EPDM 1-3.5mm to be stored under dry conditions and sheltered from weather.

# Safety pre-cautions

CONIPUR EPDM 1-3.5mm granules is after application non-hazardous.

CONICA AG Industriestr. 26 8207 Schaffhausen Switzerland Tel.: +41 52 644 3600 Fax: +41 52 644 3699 info@conica.com Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the professional competence involved in the application of the product are beyond our control.

As all CONICA guidelines maybe updated as needed, it is user's responsibility to obtain the most recent issue. Registered users can obtain the actual data sheets from our webpage. Hard copies are available upon request.